

ASPT-0309-02 Sample Test Instruction	دستورالعمل آزمون نمونه ASPT-0309-02
Materials Supplied: - One pack Sample 1 labeled as “ASPT-0309-02” including 8 specimens (app. 42×42mm) - One pack Sample 2 labeled as “ASPT-0309-02” including 8 specimens (app. 42×42mm) Parameters to be measured: - Density [gr/cm³] Test Method: ISO 1183-1 - ASTM D792 - INSO 7090, other equivalent methods. Test conditions: - Conditioning: At least 16 h normal climate (23°C and 50% r.H.) - Test Temperature: 23°C Remarks: - Treat proficiency test items in the same manner as the majority of routinely tested samples. - For both samples, three results should be submitted and each measurement should be done in different dates and each result should be the average of two replicates. Remaining samples can be used for equipment set up or substitution of one of the other specimens. - For all the mentioned parameters, results should be reported according to the specified test method. - Report data to the 4 decimal places. - PT Coordinator contact number 02185922417	نمونه‌های ارسال شده: - یک بسته Sample 1 با برچسب “ASPT-0309-02” حاوی ۸ عدد نمونه (با ابعاد تقریبی 42×42mm) - یک بسته Sample 2 با برچسب “ASPT-0309-02” حاوی ۸ عدد نمونه (با ابعاد تقریبی 42×42mm) پارامترهای مورد اندازه‌گیری: - دانسیته [gr/cm³] - روش آزمون: ISO 1183-1 - ASTM D792 - INSO 7090 و سایر روش‌های معادل - شرایط آزمون: - شرایط محیطی پیش از آزمون: حداقل 16 ساعت در شرایط محیطی عادی (23°C , 50% r.H.) - دمای آزمون: 23°C توضیحات: - نمونه‌های آزمون مهارت را همانند نمونه‌های روتین تست کنید. - برای هر نمونه باید سه نتیجه ثبت شود که هر نتیجه مربوط به اندازه‌گیری در روزهای مختلف باشد و هر نتیجه، میانگین دو تکرار باشد. - نمونه‌های باقیمانده می‌تواند برای تنظیم یا جایگزینی با یکی از نمونه‌ها استفاده شود. - برای هر یک از پارامترهای فوق، با توجه به روش آزمون انتخابی نتیجه را ثبت نمایید. - داده‌ها باید تا ۴ رقم بعد از اعشار گزارش شوند. - شماره تماس هماهنگ کننده آزمون مهارت 02185922417
Results Submission Deadline: 31. Jan. 2025	مهلت ارسال نتایج: 12 بهمن 1403