

ASPT-0309-01 Sample Test Instruction	دستورالعمل آزمون نمونه ASPT-0309-01
Materials Supplied: - 150 gr Sample 1 labeled as “ASPT-0309-01” - 150 gr Sample 2 labeled as “ASPT-0309-01” Parameters to be measured: - Melt Flow Index (MFI) [g/10min] - Melt Volume Rate (MVR) [cm³/10min] Storage conditions: Natural weather in (23 ± 2 °C) Test Method: ISO 1133 - ASTM D1238 - INSO 6980, other equivalent methods. Test conditions: Sample 1: - Preheating time: 5 minutes - Drying: 80°C / 1.5 h - Testing parameters: 190 °C/ 2.16 kg Sample 2: - Preheating time: 5 minutes - Drying: 80°C / 1.5 h - Testing parameters: 190 °C/ 21.6kg - Remarks: - Treat proficiency test items in the same manner as the majority of routinely tested samples. - For both samples, 3 result should be submitted and each measurement should be done in different dates and each result should be the average of 2 replicates. Remaining samples can be used for equipment set up or substitution of one of the other specimens. - For all the mentioned parameters, results should be reported according to the specified test method. - Report data to 2 decimal places. - PT Coordinator contact number 02185922417	نمونه‌های ارسال شده: - 150 گرم نمونه Sample 1 با برچسب “ASPT-0309-01” - 150 گرم نمونه Sample 2 با برچسب “ASPT-0309-01” پارامترهای مورد اندازه گیری: - شاخص جریان مذاب (MFI) [g/10min] - شاخص حجم مذاب (MVR) [cm³/10min] شرایط نگهداری: آب و هوای طبیعی در °C (23 ± 2) روش آزمون: ISO 1133 - ASTM D1238 - INSO 6980 و سایر روش های معادل شرایط آزمون: نمونه Sample 1: - زمان پیش گرم کردن: 5 دقیقه - خشک کردن: 80°C / 1.5 ساعت - پارامترهای آزمون: 190°C / 2.16 kg نمونه Sample 2: - زمان پیش گرم کردن: 5 دقیقه - خشک کردن: 80°C / 1.5 ساعت - پارامترهای آزمون: 190°C / 21.6kg توضیحات: - نمونه ها را همانند نمونه های روتین تست کنید. - برای هر نمونه باید سه نتیجه ثبت شود که هر نتیجه مربوط به اندازه گیری در روزهای مختلف باشد و هر نتیجه، میانگین دو تکرار باشد. نمونه های باقیمانده میتواند برای تنظیم یا جایگزینی با یکی از نمونه ها استفاده شود. - برای هر یک از پارامترهای فوق، با توجه به روش آزمون انتخابی نتیجه را ثبت نمایید. - نتایج باید تا دو رقم بعد از اعشار گزارش شوند. - شماره تماس هماهنگ کننده آزمون مهارت 02185922417
Results Submission Deadline: 31. Jan. 2025	مهلت ارسال نتایج: 12 بهمن 1403