

ASPT-0309-04 Sample Test Instruction	دستورالعمل آزمون نمونه ASPT-0309-04
Materials Supplied: - One pack Sample 1 labeled as “ASPT-0309-04” including 8specimens Parameters to be measured: - Modulus of Elasticity [MPa] Test Method: ISO 527-1,2 - ASTM D638 - INSO 764, other similar methods. Test conditions: - Test Specimens Type: 1A - Test Speed: 1 mm/min - Gauge Length: 50± 0.5mm or 75±0.5mm - It is necessary to use an extensometer. - Pre-Load: 1 MPa - Conditioning: At least 16 h normal climate (23°C and 50% r.H.) Remarks: - Treat proficiency test items in the same manner as the majority of routinely tested samples. - For sample, <u>one</u> result should be submitted and each result should be the average of <u>five</u> replicates. - For all the mentioned parameters, results should be reported according to the specified test method - Modulus of Elasticity should be reported to 1 decimal place - Specify the type of extensometer used (optical or contact). - Subcontractor activities: sample preparation was done by subcontractor - PT Coordinator contact number 02185922417	نمونه‌های ارسال شده: - یک بسته Sample 1 با برچسب “ASPT-0309-04” حاوی ۸ عدد نمونه پارامترهای مورد اندازه گیری: - مدول الاستیسیته [MPa] روش آزمون: ISO 527-1,2 - ASTM D638 - INSO 764 و سایر روش های مشابه شرایط آزمون: - نوع نمونه: 1A - سرعت انجام آزمون: 1 mm/min - طول گیج: 50± 0.5mm or 75±0.5mm - استفاده از اکستنسومتر ضروری است. - پیش لود: 1 MPa - شرایط محیطی پیش از آزمون: حداقل ۱۶ ساعت در شرایط محیطی عادی (23°C , 50% r.H.) توضیحات: - نمونه های آزمون مهارت را همانند نمونه های روتین تست کنید. - برای نمونه باید <u>یک</u> نتیجه ثبت شود که میانگین <u>پنج</u> تکرار باشد. - برای هر یک از پارامترهای فوق، با توجه به روش آزمون انتخابی نتیجه را ثبت نمایید. - مدول الاستیسیته تا یک رقم بعد از اعشار گزارش شود. - نوع اکستنسومتر استفاده شده را مشخص کنید.(نوری یا تماسی) - آماده سازی نمونه توسط پیمانکار فرعی انجام شده است - شماره تماس هماهنگ کننده آزمون مهارت 02185922417

ASPT-0309-04 Sample Test Instruction	دستورالعمل آزمون نمونه ASPT-0309-04
Results Submission Deadline: 04. Feb. 2025	مهلت ارسال نتایج: ۱۵ بهمن ۱۴۰۳

www.aryasasol.com